

PCTWORLD INTELLECTUAL PROPERTY ORGANIZATION
International Bureau

INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁶ : C08G 18/42, 18/32, 18/38, 18/66, 18/28, C09D 175/06	A1	(11) International Publication Number: WO 97/30099 (43) International Publication Date: 21 August 1997 (21.08.97)
(21) International Application Number: PCT/EP97/00579 (22) International Filing Date: 10 February 1997 (10.02.97) (30) Priority Data: 9602957.4 17 February 1996 (17.02.96) GB (71) Applicant (for all designated States except US): IMPERIAL CHEMICAL INDUSTRIES PLC [GB/GB]; Imperial Chem- ical House, Millbank, London SW1P 3JF (GB). (72) Inventor; and (75) Inventor/Applicant (for US only): FENN, David, Robert [GB/GB]; 29 Wendover Road, Burnham, Buckinghamshire SL1 7ND (GB). (74) Agent: WARD, Steven, Paul; ICI Paints, Patents & Trade Marks Section, Legal Affairs Dept., Wexham Road, Slough SL2 5DS (GB).		(81) Designated States: AL, AM, AT, AU, AZ, BB, BG, BR, BY, CA, CH, CN, CZ, DE, DK, EE, ES, FI, GB, GE, HU, IL, IS, JP, KE, KG, KP, KR, KZ, LK, LR, LS, LT, LU, LV, MD, MG, MK, MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, TJ, TM, TR, TT, UA, UG, US, UZ, VN, European patent (AT, BE, CH, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE). Published <i>With international search report.</i>
(54) Title: COATING COMPOSITION (57) Abstract A coating composition comprising a solution in a volatile organic solvent of: (i) a polyisocyanate, (ii) a reactive diluent having amine groups or blocked amine groups, and (iii) a hydroxyl functional compound which is a polyester having secondary hydroxyl groups.		

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AM	Armenia	GB	United Kingdom	MW	Malawi
AT	Austria	GE	Georgia	MX	Mexico
AU	Australia	GN	Guinea	NE	Niger
BB	Barbados	GR	Greece	NL	Netherlands
BE	Belgium	HU	Hungary	NO	Norway
BF	Burkina Faso	IE	Ireland	NZ	New Zealand
BG	Bulgaria	IT	Italy	PL	Poland
BJ	Benin	JP	Japan	PT	Portugal
BR	Brazil	KE	Kenya	RO	Romania
BY	Belarus	KG	Kyrgyzstan	RU	Russian Federation
CA	Canada	KP	Democratic People's Republic of Korea	SD	Sudan
CF	Central African Republic	KR	Republic of Korea	SE	Sweden
CG	Congo	KZ	Kazakhstan	SG	Singapore
CH	Switzerland	LI	Liechtenstein	SI	Slovenia
CI	Côte d'Ivoire	LK	Sri Lanka	SK	Slovakia
CM	Cameroon	LR	Liberia	SN	Senegal
CN	China	LT	Lithuania	SZ	Swaziland
CS	Czechoslovakia	LU	Luxembourg	TD	Chad
CZ	Czech Republic	LV	Latvia	TG	Togo
DE	Germany	MC	Monaco	TJ	Tajikistan
DK	Denmark	MD	Republic of Moldova	TT	Trinidad and Tobago
EE	Estonia	MG	Madagascar	UA	Ukraine
ES	Spain	ML	Mali	UG	Uganda
FI	Finland	MN	Mongolia	US	United States of America
FR	France	MR	Mauritania	UZ	Uzbekistan
GA	Gabon			VN	Viet Nam

5

10

15

Coating Composition

20

This invention relates to polyurethane coating compositions, their preparation and use.

25 Coatings used for the original painting of motor vehicles and for their repair are required to have very good physical properties such as hardness and resistance to water and solvents. The coating compositions are also required to have good application and
30 appearance properties so that they are easy to apply to a substrate using spray application and result in final films having a good gloss.

One class of coating compositions commonly used for these applications comprises
35 a hydroxyl functional polymer, such as a polyester or acrylic polymer, and a polyisocyanate. These two components react together after application to a substrate to form a polyurethane coating.

40 Due to environmental considerations there is a general trend in the coatings industry towards coating compositions with reduced solvent content. One way to achieve a lower solvent content is to use so-called high solids compositions. High-solids compositions are solventborne compositions which contain a relatively high level of non-volatile materials
45 such as film-forming polymer, pigments and fillers, and a relatively low level of organic solvent.

A problem with formulating high solids coating compositions suitable for use in painting motor vehicles is that the compositions can have an unacceptably high viscosity. This is because the film forming polymers traditionally used in this field have a high solution viscosity in high solids solutions. The high viscosity gives rise to problems in spray application with poor paint atomization, and poor flow out and consequent low gloss levels and poor appearance. In practice, these types of composition are formulated so as to have a predetermined viscosity to enable consistent spraying and this puts a limit on the solids content.

One way around the viscosity problem is to use lower molecular weight polymers which generally have a lower solution viscosity. However this route has limitations and disadvantages. To produce low molecular weight acrylic polymers requires the use of high levels of initiators and chain transfer agents. These initiators and chain transfer agents become less efficient at high levels and lead to the presence of high levels of recombination products which cause toxicological and film performance problems. To produce polyesters of low molecular weight, conditions must be used under which a high level of residual polyol monomer remains which can cause film performance problems.

A better approach to very high solids compositions is to use a compound known as a reactive diluent as a partial or full replacement for the polyol. These reactive diluents reduce the viscosity of the polymer solution. Particularly useful reactive diluents are blocked or hindered amines such as aspartic esters, aldimines or ketimines. Compositions containing these types of viscosity modifier together with a hydroxyl functional acrylic or polyester polymer and a polyisocyanate are disclosed, for example, in EP-A-0 531 249.

Aldimines, ketimines and aspartic esters can be used to make compositions having a good balance of viscosity and solids content. However, partial replacement of the polyol by reactive diluent leads to compositions having a very short pot-life, probably because the diluent catalyses the reaction between the polyol and the polyisocyanate. Replacement of all of the polyol by diluent improves on the pot-life problem but the compositions form brittle films with poor adhesion to a substrate, and are expensive due to the high cost of the diluents.

We have now discovered compositions which contain a polyisocyanate, an aldimine or a ketimine viscosity modifier and a particular hydroxyl containing component which have both a good viscosity/solids balance and a good pot-life and which also give films
5 having good early properties such as hardness and drying.

According to the present invention there is provided a coating composition comprising a solution in a volatile organic solvent of;
10

- i) A polyisocyanate,
- ii) A reactive diluent having amine groups or blocked amine groups, and
- 15 iii) a hydroxyl functional compound which is a polyester having secondary hydroxyl groups.

The volatile organic solvent can be any solvent which will dissolve the
20 polyisocyanate, the viscosity modifier and the hydroxyl functional compound. It can be an aliphatic or aromatic hydrocarbon such as Solvesso 100™, toluene or xylene, an alcohol such as butanol or isopropanol, an ester such as butyl acetate or ethyl acetate, a ketone
25 such as acetone, methyl isobutyl ketone or methyl ethyl ketone, an ether, an ether-alcohol or an ether-ester or a mixture of any of these.

Preferably the compositions contain less than 500 g/l of volatile organic solvent
30 based on the total composition, more preferably less than 480 g/l still more preferably less than 420g/l and most preferably less than 250g/l.

Polyisocyanates are well known in the coatings art. Polyisocyanates are compounds
35 having two or more isocyanate groups per molecule. The isocyanate groups can be blocked but unblocked isocyanates are preferred.

Suitable diisocyanates are aliphatic or aromatic diisocyanates. Examples of suitable
40 aliphatic diisocyanates are hexamethylene diisocyanate and isophorone diisocyanate. Examples of suitable aromatic diisocyanates are toluene diisocyanate and 4,4'-diphenylmethane diisocyanate.


45 Other suitable polyisocyanates include the isocyanurate trimers, allophanates and uretdiones of diisocyanates such as those described above as well as the reaction products of these diisocyanates with polyols. Polyols are compounds having three or more hydroxyl

groups. Suitable polyols include trimethylol propane, glycerol and pentaerithritol. Many such polyisocyanates are commercially available, for example under the Desmodur trade mark from Bayer or the Tolonate trade mark from Rhone Poulenc.

Polyisocyanates are preferably used in an amount such that the ratio of isocyanate groups on the polyisocyanate to the total number of hydroxyl groups and blocked or unblocked amine groups in the composition is in the range 0.7:1 to 3:1, more preferably 0.9:1 to 1.5:1.

Preferably the reactive diluent has blocked primary amine groups or hindered secondary amine groups. Examples of reactive diluents having blocked primary amine groups are aldimines and ketimines. Examples of reactive diluents having hindered secondary amine groups are aspartic esters.

Aldimines or ketimines are compounds of formula (I)
















in which n is 0 to 4, R^1 and R^2 are independently H, alkyl, cycloaliphatic or substituted alkyl, aryl or cycloaliphatic group, R^3 is aliphatic, cycloaliphatic, aromatic or araliphatic which may also contain O, N, S, or Si.

Preferred ketimines and aldimines are obtained by reaction of a diamine and an aldehyde or ketone. Preferred amines are diamines of the formula (II)



in which R is C₂₋₁₈ aliphatic, cycloaliphatic or aryliphatc. Preferred diamines are aliphatic an aliphatic diamines. Examples of suitable aliphatic and cycloaliphatic diamines are ethylene diamine, propylene diamine and cycloaliphatic diamines of the formulas;



Aldehydes and ketones suitable for use in making the aldimines and ketimines are those containing 1 to 8 carbon atoms such as propionaldehyde, butyraldehyde, isobutyraldehyde, acetone, methyl ethyl ketone, methyl isobutyl ketone, diisopropyl ketone, cyclopentanone and cyclohexanone.

One particularly preferred aldimine is Desmophen TPLS 2142 (trade mark) from Bayer.

Aspartic esters are secondary amine functional compounds made by nucleophilic addition of a primary amine to an unsaturated carboxylic acid, ester or anhydride. Examples of suitable primary amines are aliphatic primary amines such as ethylamine, propylamine and butylamine. Preferred amines are diamines such as ethylene diamine, hexane-1,6-diamine and 4,4'-methylenebis (2-methyl) cyclohexane amine. Examples of suitable unsaturated acids, esters and anhydrides are maleic and fumaric acid, maleic anhydride and maleic and fumaric acid esters such as dimethyl, diethyl and dibutyl maleates and fumarates.

Preferably the hydroxyl functional compound has a molecular weight of less than 5000, more preferably less than 2500 and most preferably less than 2000. Preferably the secondary hydroxyl groups on the hydroxy functional compound are the product of a reaction between a carboxylic acid group and an epoxide group.

Preferably the hydroxyl functional compound is the reaction product of a polyfunctional carboxylic acid and a monoepoxide, and so has secondary hydroxyl groups arising from the reaction of the acid groups on the polycarboxylic acid with the epoxy group on the monoepoxide.

Preferred monoepoxides are glycidyl esters of C2-C20 alkanolic acids, preferably C8-C9 tertiary carboxylic acids such as versatic acid. One particularly suitable monoepoxide is Cardura E10TM.

The polyfunctional carboxylic acid can be a polyester with two or more carboxylic acid groups, preferably two to four carboxylic acid groups, more preferably two or three such groups. Polyesters are compounds containing more than one ester group. Acid functional polyesters can be made by conventional methods from a mixture of polyols, diacids and anhydrides. One preferred acid functional polyester can be made by reaction of a polyol with a carboxylic acid anhydride. Polyols are compounds with more than one

hydroxyl group. Preferably the polyol has from two to four hydroxyl groups per molecule and more preferably it is a diol or a triol, diols being particularly preferred. Preferably the polyol has a molecular weight of 66 to 150. Examples of suitable polyols are ethylene glycol, propylene glycol, neopentyl glycol, hexane-1,6-diol, glycerol, trimethylol propane and pentaerythritol. Preferred anhydrides are cyclic internal anhydrides of dicarboxylic acids such as maleic anhydride, succinic anhydride, phthalic anhydride and hexahydroxyphthalic anhydride.

Preferably the reaction between the anhydride and the polyol is carried out substantially stoichiometrically so that one anhydride molecule reacts with each hydroxyl group on the polyol. The resulting polyfunctional acid compound has substantially the same number of acid groups as the polyol had hydroxyl groups. Because the hydroxyl/anhydride reaction occurs at a lower temperature than the carboxyl/hydroxyl or transesterification reactions, there are few side reactions and the molecular weight of the product can be controlled.

The reaction between the polyol and the anhydride can be carried out by dissolving the components in an organic solvent and then heating the solution preferably to between about 100 and 130°C for between about 1 and 3 hours so as to produce the polyfunctional carboxylic acid.

The reaction between the polyfunctional carboxylic acid and the monoepoxide can be carried out by adding the monoepoxide to a solution of the polycarboxylic acid in a suitable organic solvent in an amount so as to react each of the hydroxyl groups on the polyol with an epoxide group, and heating the mixture to between about 130 and 160°C for between about 2 and 12 hours.

The compositions can also contain catalysts for the isocyanate-hydroxyl reaction. Suitable catalysts include tin catalysts such as dibutyl tin dilaurate and amine catalysts such as triethylamine. The compositions can also contain other conventional paint additives such as, pigments, fillers, UV absorbers and flow aids.

Preferably the non-volatile weight ratio of the reactive diluent to the hydroxyl functional polymer in the composition is 10:90 to 90:10, more preferably 60:40 to 40:60.

The compositions can be made by mixing the components, optionally dissolved in organic solvent, in any order. Because of the limited pot-life of the compositions, they are preferably made by adding the polyisocyanate, to the reactive diluent and then adding the polyol.

The coating composition of the invention can be applied to the surface of a substrate and then allowed or caused to dry and cure. According to the present invention there is provided a process for coating a substrate which comprises the steps of applying a layer of a coating composition according to the present invention to a surface of the substrate and thereafter causing or allowing the layer to cure.

The coating composition can be applied by conventional means such as by brush, roller or spray, preferably spray. The substrate can be for example, metal, plastic, wood or glass. The compositions are particularly useful for refinishing motor vehicles.

The applied layer can be allowed to cure at ambient temperature in the case where the hydroxyl polymer and crosslinker react together at ambient temperatures. Alternatively the layer can be baked at elevated temperatures, for example 50-120°C to accelerate curing. Drying and curing typically takes between 5 minutes and 24 hours depending on the ambient conditions and on the particular components used. Conveniently it takes about 15 minutes to about 5 hours.

According to the present invention there is also provided a coated article obtainable by the process.

The invention will now be illustrated by means of the following examples.

1. Preparation of Polyesters 1 to 4 according to the invention.

5 1.1 Polyester 1 having secondary hydroxyl groups.

A mixture of neopentyl glycol (56.5 parts) and hexahydroxy phthalic anhydride (167.4 parts) were heated under nitrogen to about 95C so as to melt the components. The
10 molten mixture was stirred and the temperature was slowly raised until an exotherm occurred at about 130C. At this point, heating was stopped and the temperature went up to 170C, then down to 150C whereupon heating was resumed and the mixture was held at
15 150C for 1 hour. The mixture was then allowed to cool for 1h. The mixture was heated back up to 150C, Cardura E10™ (glycidyl ester of a C8-9 carboxylic acid from Shell, 276.1 parts) was added dropwise over a period of 3.5 hours and the mixture was allowed to cool to room temperature and left overnight. The mixture was heated to 150C for a further 7
20 hours before being allowed to cool to room temperature. Butyl acetate (55 parts) was added to give a theoretical non-volatile solids content of 90%. The final measured acid value was 0.5 mgKOH/g based on non-volatile content. The weight average molecular
25 weight as measured by g.p.c was 719.

30 1.2 Polyester 2 having secondary hydroxyl groups

A mixture of trimethylol propane (49.3 parts) and hexahydroxy phthalic anhydride (170.1 parts) were heated under nitrogen to about 60C so as to melt the components. The
35 molten mixture was stirred and the temperature was slowly raised until an exotherm occurred at about 150C. Heating was stopped and the temperature went up to 180C, and back down to 150C. Heating was resumed and the mixture was held at 150C for 1 hour. The mixture was allowed to cool for 1 hour. The mixture was heated back up to 150C,
40 Cardura E10™ (glycidyl ester of a C8-9 carboxylic acid from Shell, 280.6 parts) was added dropwise over a period of 3 hours and the mixture was allowed to cool to room temperature and left overnight. The mixture was heated to 150C for a further 7 hours
45 before being allowed to cool to room temperature. Butyl acetate (55 parts) was added to give a theoretical non-volatile solids content of 90%. The final measured acid value was

1.6mgKOH/g based on non-volatile content. The weight average molecular weight as measured by g.p.c was 967.

5

1.3 Polyester 3 having secondary hydroxyl groups

A mixture of neopentyl glycol (57.3 parts) and phthalic anhydride (163.0 parts) were heated to about 80C until the components melted. The molten mixture was stirred and the temperature was slowly raised until an exotherm occurred at about 110C. The temperature went up to 160C, and down to 150C. Cardura E10™ (glycidyl ester of a C8-9 carboxylic acid from Shell, 279.7 parts) was added dropwise over a period of 1.5 hours. The mixture was allowed to cool for 1 hour and then heated back to 150C for a further 2.5 hours before being allowed to cool to room temperature. Butyl acetate (55 parts) was added to give a theoretical no-volatile solids content of 90%. The final measured acid value was 1.1mgKOH/g based on non-volatile content. The weight average molecular weight as measured by g.p.c. was 791.

25

1.4 Polyester 4 having secondary hydroxyl groups

A mixture of cyclohexane dimethanol (75 parts) and hexahydroxy phthalic anhydride (160.4 parts) were slowly heated under nitrogen with stirring. At about 170C an exotherm occurred and the temperature went up to 180C, after which the temperature was reduced to 150C. Cardura E10™ (glycidyl ester of a C8-9 carboxylic acid from Shell, 264.6 parts) was added dropwise over a period of 1.5 hours. The mixture was allowed to cool at room temperature for 1 hour and then heated back to 150C for a further 2.5 hours before being allowed to cool to room temperature. Butyl acetate (55 parts) was added to give a theoretical non-volatile solids content of 90%. The final measured acid value was 3.5 mgKOH/g based on non-volatile content. The weight average molecular weight as measured by g.p.c. was 749.

45

1.5 Polyester 5 having secondary hydroxyl groups

A mixture of neopentyl glycol (312 parts) and hexahydroxy phthalic anhydride (924 parts) were added to Solvesso 100™ (aliphatic hydrocarbon solvent from Exxon, 660 parts) and the mixture was heated to 90C. An exotherm occurred, after which the temperature was raised to 120C. The mixture was stirred at 120C for 2 hours. The temperature of the reaction mixture was raised to 150C and Cardura E10™ (glycidyl ester of a C8-9 carboxylic acid from Shell, 1416 parts) was added over a period of 3 hours and the mixture was allowed to cool to room temperature and left overnight. The mixture was heated to 150C and stirred for a further 7 hours before being allowed to cool to room temperature.

2 Preparation of polymers not according to the invention

2.1 Comparative Polyester 6 having primary Hydroxyl Groups

A mixture of trimethylol propane (306.85 parts), hexahydroxy phthalic anhydride (320.75 parts) and neopentyl glycol (52.31 parts) were heated slowly under nitrogen over about 2.5 hours to about 210C with stirring in a vessel equipped with a Dean and Stark separator for removing water. The mixture was held at between 200 and 210C for 4.5 hours whilst the water produced in the reaction was removed, until the final measured acid value was 28.6mgKOH/g based on non-volatile content. About 130ml of water was removed in this time. The mixture was allowed to cool to below 120C and 277.6 parts of butyl acetate was added to give a final theoretical non-volatile solids content of 70%. The weight average molecular weight as measured by g.p.c. was 1738.

2.2 Acrylic Polymer 7

A mixture of 2-ethylhexyl acrylate (17.78 parts), butyl acrylate (16.16 parts) styrene (13.13 parts) hydroxy isopropyl methacrylate (19.3 parts), azodiisobutyronitrile (Vazo 67™ from DuPont, 2.33 parts), primary octyl mercaptan (2.33 parts) and butyl acetate (7.42 parts) were added slowly over 3 hours to a refluxing mixture of Solvesso 100™ (10.57 parts) and butyl acetate (10.57 parts) with stirring under nitrogen. The mixture was stirred

for 15 minutes and a peroxy initiator (Trigonox 21sTM from Akzo, 0.116 parts) was added. The mixture was stirred for a further 1 hour and further Trigonox 21s (0.116 parts) was added. The mixture was stirred for a further hour and then allowed to cool to room temperature. The weight average molecular weight was 6100.

3. Coating compositions 1 and 2

Two coating compositions were prepared comprising a hydroxyl functional resin, an aldimine (Desmophen TPLS 2142TM from Bayer AG), a polyisocyanate (HDT LVTM, from Rhone-Poulenc) and butyl acetate. These were made so as to have a viscosity of 25s BSB4 cup.

Composition 1 comprised Polyester 1 from paragraph 1.1 above at a non-volatile weight ratio of 1:1 hydroxyl functional resin to aldimine. Comparative composition 2 was similar but contained a known, commercially available hydroxyl functional reactive diluent K-Flex 188TM (from King Industries) instead of hydroxyl functional Polymer 1. The compositions are summarised below in Table 1.

Table 1

	Composition	
	1	2
Aldimine	32	29.2
Polyisocyanate	56	61.7
Polyester 1	35.5	-
K-Flex 188	-	29.2
Butyl acetate	32.4	36

4. Testing

The compositions were applied to clean glass sample panels using a 150m block spreader. One sample panel of each was allowed to stand at room temperature (20C) and the dust-free times of the films were measured by recording the time at which dust would

no longer stick to the film surface when attempt was made to remove it with a small paint brush. A second sample panel of each composition was baked at 60C for 30 minutes and the film hardness was measured using a Konig hardness tester after standing for 1 hour. The viscosities of the bulk compositions were measured in seconds using a BSB4 cup 3 hours after making them as a guide to their pot-life. The results are given in Table 2 below.

Table 2

	Composition	
	Invention	Comparative
	1	2
3h Viscosity Rise (s)	20	51
Dust free time (mins)	30-45	60-75
Hardness 1h after bake (s)	31	12

These results show that composition 1 according to the present invention shows better pot-life, faster tack free times at ambient temperature and improved hardness after baking.

5. Coating Compositions 3 to 6

Four coating compositions were made comprising Polyesters 2 to 4 and Acrylic Polymer 7, a 50/50 by weight mixture of two polyisocyanates (HD 100TM from Olin and HDT LVTM), an aldimine (Desmophen TPLS 2142TM) and butyl acetate. The compositions were made so as to have a weight ratio of polymer to aldimine of 1:1. The ratio of the number of hydroxyl and imine groups to the number of isocyanate groups was 1:1 in each case. The compositions were made to a theoretical solids content of 80%. The compositions are detailed in Table 3 below.

Table 3

Components	Composition			
	3	4	5	6
Polyester 2	35.3	-	-	-
Polyester 3	-	35.3	-	-
Polyester 4	-	-	35.5	-
Acrylic Polymer 7	-	-	-	45.9
Polyisocyanate	56.4	56.4	56	55.8
Aldimine	31.8	31.8	32	32.1
Butyl acetate	26.5	26.5	26.4	16.2

The compositions were tested for initial viscosity. Additional butyl acetate (3 parts) was added to Composition 6 in order to bring its viscosity down to 25 s BS B4. The compositions were tested for viscosity rise after 1 hour, dust-free time and hardness after low-bake as described in paragraph 4 above. The results are given in Table 4 below.

Table 4

Test	Composition			
	3	4	5	6
Initial Viscosity (80% solids)	26	25	25	28
1h viscosity rise (s)	11	51	8	3
Dust free time (min)	30-40	30-40	30-40	60-70
Hardness after low bake (s)	38	32	36	still tacky

The results show that the compositions according to the invention show better dust free times and very much better hardness after baking than the composition containing acrylic polymer 7.

6. Compositions 7 to 10 containing Polyesters 1 to 4 and Acrylic Polymer 7.

Four compositions were made comprising polyesters 1 to 4, together with acrylic polymer 7, a 50/50 blend of two polyisocyanates, (HDT LVTM and HD100TM), an aldimine (VPLS 2142TM) and butyl acetate solvent. The compositions were made so as to have a weight ratio of polymer to aldimine of 1:1. The ratio of the number of hydroxyl and imine

groups to the number of isocyanate groups was 1:1 in each case. The compositions were made to a theoretical solids content of 80%. The compositions are detailed in Table 5 below.

Table 5

Components	Composition			
	7	8	9	10
Polyester 1	17.8	-	-	-
Polyester 2	-	17.7	-	-
Polyester 3	-	-	17.7	-
Polyester 4	-	-	-	17.8
Acrylic Polymer 7	22.8	22.8	22.8	22.9
Polyisocyanate mixture	56	56.2	56.2	56
Aldimine	32	31.9	31.9	32
Butyl acetate	21.4	21.4	26.4	21.4

The compositions were thinned to 25s BS B4 and tested for viscosity rise after 1 hour, dust-free time and hardness after low-bake as described in paragraph 4 above. The results are given in Table 6 below.

Table 6

Test	Composition			
	7	8	9	10
Added Solvent to 25s BS B4	0	2	2	1
1h viscosity rise (s)	7	7	18	7
Dust free time (min)	30-40	30-40	20-30	30-40
Hardness 1h after bake (s)	29	36	53	32

Compositions 11 to 14 containing Polyester 1, Comparative Polyester 6 and ketimines.

Four compositions were made comprising Polyester 1 and Comparative Polyester 6, a 50/50 blend of two polyisocyanates, HDT LVTM and HD100TM, a ketimine (Desmophen VPLS 2965TM from Bayer AG) and butyl acetate solvent. The compositions were made so

as to have a weight ratio of polymer to aldimine of 1:1. The ratio of the number of hydroxyl and imine groups to the number of isocyanate groups was 1:1 in each case. The compositions were made to a theoretical solids content of 80%. The compositions are detailed in Table 7 below.

Table 7

Components	Composition	
	11	12
Polyester 1	37.7	-
Polyester 6	-	40
Polyisocyanate mixture	52.2	64
Ketimine	33.9	28
Butyl acetate	26.2	18

The compositions were tested for viscosity rise after 1 hour, dust-free time and hardness after low-bake as described in paragraph 4 above. The results are given in Table 8 below.

Table 8

Test	Composition	
	12	14
1h viscosity rise (s)	7	73
Dust free time (min)	90-120	30-45
Hardness 1h after bake (s)	36	109

The results clearly show that Composition 12 has an acceptable pot-life while Composition 14 has an unacceptably short pot-life.

8. Primer Composition

8.1 Fillers Heucophos ZPA™ (762.1) and Byk 110™ (36g), Mistrion Monomix™ (329.48g) and Microdol Extra™ (658.96g), were added slowly in the order given to a mixture of Polyester 3 from 1.3 above (160.87g) and a solvent mixture (60g) comprising equal quantities of xylene, butyl

acetate and propylene glycol monomethyl ether in a Dispermat HSD™ high speed disperser. A pigment mixture of Bentone SD2™ (12.6g) and titanium dioxide (128.64g) was added slowly and the mixture was dispersed for a further 45 minutes. Further solvent mixture (544g) was added to form a pigmented primer base.

8.2 Ketimine (Desmophen VPLS 2965™ from Bayer AG; 8.65 parts) and a polyisocyanate (HDT 90™, from Rhone-Poulenc, 14.35 parts) were added to the composition (77 parts) and the composition was thinned to 25 seconds BSB4 with butyl acetate.

8.3 The composition was applied to clean glass sample panel using a 150m block spreader, the panel was allowed to stand at room temperature (20°C) and the dust-free time of the film was measured to be 25 minutes by recording the time at which dust would no longer stick to the film surface when attempt was made to remove it with a small paint brush. The viscosity of the bulk composition was measured using a BSB4 cup 0.5 hours after making it as a guide to its pot-life to be 43s.

Claims


5 1 A coating composition comprising a solution in a volatile organic solvent of,

- 10 i) a polyisocyanate,
ii) a reactive diluent having amine groups or blocked amine groups, and
15 iii) a hydroxyl functional compound which is a polyester having secondary hydroxyl groups.

2. A composition as claimed in Claim 1 in which the ratio of the isocyanate groups on the polyisocyanate to the total number of hydroxyl groups and blocked and
20 unblocked amine groups in the composition is in the range 0.7:1 to 3:1.

3. A composition as claimed in Claim 1 or Claim 2 in which the reactive diluent is an aldimine, a ketimine or an aspartic ester.

25 4. A composition as claimed in claim 3 in which the reactive diluent is an aldimine or ketimine which is the reaction product of a diamine of the formula (II)



30 in which R is C₂₋₁₈ aliphatic, cycloaliphatic or arylphatic, and an aldehyde or ketone.

35 5. A composition as claimed in claim 4 in which the aldehyde or ketone has 2 to 8 carbon atoms.

6. A composition as claimed in any one of claims 1 to 5 in which the hydroxyl functional compound has a molecular weight of less than 5000.
40

7. A composition as claimed in any one of claims 1 to 6 in which the secondary hydroxyl groups on the hydroxy functional compound are the product of a reaction
45 between a carboxylic acid group and an epoxide group.

8. A composition as claimed in any one of claims 1 to 7 in which the hydroxyl functional compound is the reaction product of a polyfunctional carboxylic acid and a monoepoxide.
- 5 9. A composition as claimed in Claim 8 in which the monoepoxide is a glycidyl ester of a C8-C9 tertiary carboxylic acid.
- 10 10. A composition as claimed in claim 8 or claim 9 in which the polyfunctional carboxylic acid is a polyester with two or more carboxylic acid groups.
- 11 11. A composition as claimed in any one of claims 8 to 10 in which the polyfunctional carboxylic acid is the reaction product of a polyol and an anhydride.
- 15 12. A composition as claimed in Claim 11 in which the polyol has from 2 to 4 hydroxyl groups.
- 20 13. A process for preparing a composition as claimed in Claim 1 which comprises mixing
- 25 i) a polyisocyanate,
- ii) a reactive diluent having amine groups or blocked amine groups, and
- 30 iii) a hydroxyl functional compound which is a polyester having secondary hydroxyl groups,
- optionally dissolved in organic solvent, in any order.
14. A process for coating a substrate which comprises the steps of applying a layer of a coating composition according to Claim 1 to a surface of the substrate and thereafter causing or allowing the layer to cure.
- 35 15. A coated substrate obtainable by the process of Claim 14.

40

45

INTERNATIONAL SEARCH REPORT

National Application No

PCT/EP 97/00579

A. CLASSIFICATION OF SUBJECT MATTER

IPC 6 C08G18/42 C08G18/32 C08G18/38 C08G18/66 C08G18/28
C09D175/06

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 6 C08G

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	EP 0 531 249 A (BASF CORP) 10 March 1993 cited in the application see claims 1,7,10,17 see page 6, line 3 - line 8 see examples 11-14	1
A	EP 0 014 808 A (FORD MOTOR CO ; FORD WERKE AG (DE); FORD FRANCE (FR); FORD MOTOR CO) 3 September 1980 see claims 1-4 see page 4, line 8 - line 27	1
A	DE 25 28 377 A (PROLUX PAINT MANUFACTURERS LTD) 15 January 1976 see claims 1-7	1

☐ Further documents are listed in the continuation of box C.

☒ Patent family members are listed in annex.

* Special categories of cited documents :

- * "A" document defining the general state of the art which is not considered to be of particular relevance
- * "E" earlier document but published on or after the international filing date
- * "L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- * "O" document referring to an oral disclosure, use, exhibition or other means
- * "P" document published prior to the international filing date but later than the priority date claimed

- * "T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
- * "X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
- * "Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.
- * "&" document member of the same patent family

Date of the actual completion of the international search

12 May 1997

Date of mailing of the international search report

26.05.97

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+ 31-70) 340-2040, Tx. 31 651 epo nl,
Fax (+ 31-70) 340-3016

Authorized officer

Van Puymbroeck, M

INTERNATIONAL SEARCH REPORT

Information on patent family members

Application No

PCT/EP 97/00579

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
EP 0531249 A	10-03-93	US 5214086 A CA 2076910 A JP 5271617 A	25-05-93 05-03-93 19-10-93
EP 0014808 A	03-09-80	CA 1144689 A JP 55092772 A	12-04-83 14-07-80
DE 2528377 A	15-01-76	CA 1054285 A GB 1509417 A US 3991003 A	08-05-79 04-05-78 09-11-76

THIS PAGE BLANK (USPTO)